

A Review Study on the Aggregate Properties of Demolished Concrete

Patil Uday Shankar^{1*} Dr. Ramana Reddy Y.² Dr. Indrajeet Yadav³

¹ Research Scholar, University of Technology, Jaipur

² Professor, Department of Civil Engineering, University of Technology, Jaipur

³ Professor, SMSMP Institute of Technology and Research, Akluj

Abstract – *The need for demolition, repairs and renewal of concrete and masonry structures is rising all over the world, more so in the developing countries. It is highly desirable that the waste materials of concrete and bricks generated after the demolition of old structures are reutilized in an effective manner to reduce the environmental damages caused by excessive reckless quarrying for earth materials and stones. Also, this will reduce pressure on finding new dumping ground for these wastes, thus further saving the natural environment and ecosystem.*

The present investigation is focused on use of demolished concrete in order to reduce construction cost and resolve housing problems faced by the low-income communities of the world. The crushed demolished concrete is segregated by sieving to obtain required sizes of aggregate. Several tests were conducted to determine the aggregate properties before recycling it into new concrete. This investigation shows that the demolished concrete that are obtained from site make good quality concrete.

Keywords – Aggregate, Properties, Demolished Concrete

-----X-----

INTRODUCTION

Building material and the most important civil engineering component is concrete. There would be little other reason in the future to use concrete as a construction material. Beside the strength of the concrete, the durability, functionality, and a fair life of the concrete are all very important. For example, concrete should not only have a high force but also minimum shrinking and creeping characteristics on pre-stressed bridges of concrete. Concrete should offer complete fatigue for the ground and equipment center, ashore, bridges and structure, roads and airports. The concrete has a good thermal fracture resistance for high temperature-prone radioactive containers. In the development and function of (HPC) high-performance concrete, a focused approach was adopted to optimize the material's potential to increase its service life by about 100 years and its usage for 40 to 50 years and to provide adequate performance in uncommon harsh conditions. Motivating sustainable development requires the careful use of natural capital and the best recycling through research and upgrading of structures. The use of reuse aggregates in concrete manufacturing is one such possibility.

The necessity to search for additional aggregate sources leads to increased demand and a decline in the supply of concrete aggregates. Constant assessment is made of the ecological nature of building items. The use of readily available cement as a source aggregate for new concrete saves ecosystem money and reduces waste demands. The concept of sustainable building efficiency covers the responsible use of natural resources and optimum recovery of building waste via research and development. The use of recycled aggregates in concrete building is one such possible reason.

FINE AGGREGATE

Scarcity of Natural Aggregate

Concrete is typically grown on alluvial rivers with gravel and sand. The goods are widely and relatively cost-effective and thus often used for production. They also produce excellent concrete because to their physical characteristics such as shape, gradation, etc. Naturally over millions of years, these deposits have developed. The deposits were misused. There's little sand. Excessive sand removal leads to contamination of water and environmental problems. Some state governments prohibit mining

for the following purposes: (i) Excessive dredging of sand in the river bed is harmful for the ecosystem. (ii) the level of groundwater is influenced by the huge riverbank holes. (iii) Excess sand increases the deterioration of the adjacent areas. It is frequently demonstrated that the foundation of the bridges was exposed to the presence and protection of the bridges, due to the incorrect lifting of sand over the substructure.

Need for Recycled Concrete Aggregate (RCA)

In some areas, sand removal from river bottoms was banned by the authorities. The characteristics of sand and minerals that may be used must then meet the required criteria.

Dams are currently constructed in any river. These characteristics erode quite fast today. No nice sand ready. No excellent sand. Shipping expenses are greater when excellent sand has to be transported over a long distance. Mica, coal, fossils and other chemical contaminants are found also in the sand of the river. More than every proportion of the contaminants in the sand makes concrete jobs meaningless. Sanding materials such as bones, eggs, etc. decrease the stupendousness of the concrete. The sludge of the river sand reduces the strength of concrete and maintains moisture and slows down the concrete curing time.

Therefore, an alternative sand replacement material is urgently required. One of these solutions is the recycled concrete aggregate. The "recycled concrete aggregate" (RCA) is a common misunderstanding about rock quarry screening. RCA is a fine replacement aggregate that may be utilized in the manufacturing of concrete. However, RCA says in this study that destroyed concrete is utilized and broken to provide new sand for use in structural cement such in bridges, floors, etc.

Recycled Concrete Aggregates

Reconstructive aggregates are already being utilized more and more in production. In the next years, the RCA will be increasingly prevalent. Different materials for the processing of leftover concrete may be utilized. Projects of demolition are popular. Often concrete structures such as buildings, bridges, highways and roads have been smashed to reuse or destroy property after time throughout their usage. Further environmental accidents such as avalanches, floods and tornados also resulted from any sources of dispersion. These are the two reasons why surplus materials may be handled in some way. A second study shows that only 10 percentiles of demolition and construction debris produced yearly by the United Kingdom are processed into aggregate for mainly carry-overs. The use of the RCA in concrete structures is another potential outlet for the chemical. Various studies were conducted on valued and hardened cement soil to evaluate the impacts of RCA. However, RCA concrete is insufficiently accessible for durability

or long-term display. There is a tendency to decrease general concern that the use of RCA for actual activities may be endangered. RCA utilizes the demolition product for civil construction of concrete and fired clay brick. Reuse of trash is also dissipated and the distance between smashes granite new aggregates is minimized. The yearly demolition rate in major cities presently rises from 1 to 2 percent while the number of waste construction materials generated in India has not been measured adequately.

Now traction is collected from the recovered concrete aggregate. In the next several years, the RCA will be increasingly prominent. Different sources of leftover concrete may be utilized for manufacturing. The most popular demolition projects. Limited concrete structures, such as buildings, bridges, walkways and roads, may be degraded to substitute or change the landscape for a certain length of time. Such waste streams frequently comprise natural phenomena like floods, avalanches and tornadoes. These two contribute in any way to dealing with huge quantities of trash.

A recent study showed that demolition and construction waste had been aggregated for road refills for the majority of the two million tons collected yearly by the United Kingdom. The use of RCA in concrete buildings is another potential outlet for this chemical. Several investigations on the effects of RCA on fresh and hardened concrete products have been undertaken. However, RCA concrete is of very little durability or long-term effectiveness. Apart from the widespread worry that the use of RCA might endanger practical efficiency, its wider usage has also decreased.

RCA utilizes concrete and burned brick masonry as the aggregate component of removal. Reuse of demolition debris recycling and assistance for reducing the gap between demand and supply of crushed fresh granites. While the amount of material produced in India has not been properly measured, in large cities the present yearly demolition rate is estimated at 1% to 2%.

This is mainly explained by:

- demolition of structures that have become obsolete, whether due to vital functions or a structural deterioration.
- Building destruction to enhance economic performance (through new construction)
- Waste construction materials produced by natural disasters such as storms, cyclones, flood and conflict – damage inflicted.

The bulk of wastes generated by demolition methods are dispersed via disposal as landfill or for land recovery. But the location of residual materials, flexibility and land breadth are limited with demand for land increasing day by day. Furthermore, freight

expenses are a major problem for disposal. Reusing demolition debris thus appears to be an effective alternative, but concrete for new buildings as a whole will be the most appropriate and widely used. A variety of European countries (in particular Germany, England and the Netherlands) and Japan have been trying since World War II to study and utilize demolition materials in the construction of civil engineering works.

Recycling concrete is a very simple process. This means that the existing concrete of a certain scale and consistency content is broken, removed and broken up. The quality of concrete recycled concrete aggregates is highly dependent on the quality of the recycled contents. Steel removal may be an issue. Steel refurbishment and other embedded items should be removed in order to prevent contamination of other components.

In the current facility, recycled concrete compounds of various sizes were manufactured, including 20 mm to 10 mm, 10 mm to 5 mm and <5 mm primary or secondary crusher and screens. The percentage of concrete that is crushed below 5 mm is separated separately and stitched by I.S. The piece is 4.75 mm long. I.S. Sieves were used as a recycled cement aggregate to complement natural sands.

The use of RCA in Ontario is becoming more widespread as more information of outcomes is made available and fewer natural aggregates are becoming more often used politically. Organizations like as Aggregate Recycling Ontario, who promote the use of RCA, have begun some municipal process modifications throughout Ontario. Bill 56 has just been introduced by the Legislative Assembly of Ontario. The proposal aims at prohibiting the use of virgin materials to limit programs in the public sector. In the past, offers that propose the use of recycled material must be rejected on that basis. The proposal was drawn up in the first and second reading houses and sent to the Standing Financial and Economic Affairs Committee; (Legislative Assembly of Ontario, 2013).

RCA is considered to be the most prevalent technique in Ontario for complete form material. This comprises the use of the granular floor foundation, rear trench fill materials, planned filling, sub-grade stabilization, concrete sheet filling and shoulder paving development (Aggregate Recycling Ontario, 2011).

In 2007, Ontario consumed about 13 million tons of RCA. This corresponds to around 7% of the total used in that year. Most of this RCA was used for road construction, as stated above (MNR, 2010). RCA is currently not extensively utilized in Ontario concrete production.

RCA is a commodity with a high future availability that really surpasses production. This supply comprises of the existing structure of concrete, ultimately demolished. Although one of the major issues in this broad spectrum is the creation of a concrete

composed of many components. These variables are based on structural circumstances, necessary components, year of concrete manufacture and many other considerations. The extensive change in the structure of the concrete causes a comparable alteration to the RCA owing to the concession of concrete. Because of the wide variety of RCA products, some materials are appropriate for the production of high-quality cement and other materials that may damage the performance of any concrete. Between these two serious RCAs, there exist wide ranges of RCAs that differ in specific performance.

Whilst some RCAs may be impossible to achieve in concrete in this range, they are always regarded acceptable as granular contents in the filler or foundation applications.

Inherent variability of the RCA creates issues between the Canadian specifications and concrete farmers and occasionally leads to the complete avoidance or limitation of lean concrete use of RCA or other comparable low-demand applications. Several experiments in concrete, Maruyama, Sato, Fonseca, De Brito, Evangelista, and Olarunogo, and Padayachee have demonstrated the potential to lose compressive strength and resilience with usage of RCA (2005). (2002). Limiting the use of RCA is generally regarded as a reasonable strategy for reducing the hazards in this previous study.

In previous research, an RCA classification system has been created at the University of Waterloo, enabling different RCAs to be categorized for the best potential application. The applications range from structural reinforced concrete to the filling of goods merely. The approach is intended to make categorization rely mainly on aggregate testing. This allows the classification of RCA without knowing the specific origins, since the details for certain RCA are frequently not apparent. The system developed is a very excellent beginning to build a large-scale platform for the use of existing and prospective RCA in the industry.

Previous study has developed an RCA categorization system at the University of Waterloo, which identifies various RCAs for optimum usage. These applications differ from the use solely of reinforced structural cement filling material. The method was intended to mostly rely on aggregate testing for the categorization. This allows you to categorize without knowing the root concrete of RCA, since that information for a specific RCA is likewise unknown. An important step in establishing a widely established industrial source network that ensures a considerably more efficient use of current and future RCAs. A significant step forward is the implementation procedure.

Internal Curing

Internal curing offers numerous benefits of various concrete mixes. All of these benefits include reductions in rubber shrinkage, self-drying (and associated cracking) and hydration of rich compounds, improving compression power in later years and reduced concrete transport characteristics. Many of these benefits improve the hardness of rich compounds of concrete. Increasing water availability in comparison to the natural aggregate has enhanced the ITZ effect of internal treatment reservoirs (Bentz & Weiss, 2011).

Lightweight aggregates are also utilized for internal treatment (LWA). The three most important criteria for the inner curative agent comprise in decreasing order of significance: suitable desorption at about 93 per cent RH, partial distance in the combination of less than 2-3 mm and the sufficient absorption capability for supplying water. The fine LWAs are all three of these situations. LWAs have an astoundingly high vacuum material that allows them to absorb water. Usually, the quantity of LWA in internal concrete is proportionate such that binder-rich mixes are fully hydrated with plenty of water. In general, the size of the fine LWA is small enough to spread across the whole cement matrix. The idea of the cushioned paste volume is the basis of the technique. Many LWAs also support the disease and make it a pioneer in internal therapy. Addresses more features of desorption.

In many studies in the literature, the effectiveness of fine RCA as an internal healing agent has been examined. As the sole healing agent inside, the decrease in autogenous shrinkage resulted in significant loss of strength and little benefits. RCA and LWA mixes have nonetheless demonstrated similar results to low internal curing of LWA. For author's knowledge, the use of ground RCA in internal care services was not explored.

Concrete Batching Procedure

Several alternative batching methods have been used throughout the concrete production for a number of distinct reasons. The weather, kind of mixer, mixing or further cement material to be utilized as well as the distance from the batching factory, The RCAs have been subject to sophisticated batching procedures as to the high absorption of the material. These techniques are frequently employed in order to improve the functional efficiency of hardened concrete by checks on the initial usage of additional water for the concrete mix. Figure 1.1 shows the three batching techniques utilized for the production of RCA concrete.




Figure 1.1: A) CAC Concept Guidance, B) Butler, C) Two Stage Mixing Summary of Batching Procedures

Ferreira et al. investigated the effect of RCA pre-saturation on the use of RCA in building demolition (2011). Based on a timed immersion according to prior absorption experiments, the research found that RCA reached about 80 percent of the absorption potential before it was combined. The optimum humidity was evaluated to reduce mixed water retention and to avoid bleeding.

Process A) is concerned with the manufacture of natural and non-admixture regular concrete. B)C) A) B) 26 The CAC includes information on the nature of concrete mixes and their administration. (Cyprus, Czech Republic, CA). This involves covering the drum with 10% of the mixing water. It then adds all the stiffness to 80% of the water and then puts the remaining 10% of the water in the final mix until it is melted. Procedure) relates to the usage of RCA in the RCA pre-saturated Butler et al research (Butler et al., 2013b). This implies that the already absorbing cough RCA is combined along with the mixed water of one-third. The little cement and asphalt are also combined with two-thirds of the water. C) method for coarse RCA has also been developed by Tam et al. Before injecting cement, it was the primary purpose of the soil water aggregates to create a surface slurry to strengthen interfaces between the aggregate and the concrete paste, and to combine it with half the mixing water and the remainder of the mixing water. In comparison to the cement added via a traditional blending method comparable to procedure A, the pressure forces of RCA concrete were elevated early and later.

Application of Recycled Aggregates

Recycled aggregates are utilized as a concrete bolt and gutter mixture in Australia. The 10mm recycled and recycled sand is utilized by Building Innovation & Construction Technology in Sydney's Lenthall Street Scheme (1999).

According to Recycled Aggregate Products (2001), the market development reports showed greater stabilization and improved floors for structure building work than natural sub-structure aggregates that recycled aggregates are utilized as a granular basis for road building construction. Recycled aggregates may be utilized in embankment filling. The rationale for its use in retention is the same as for the construction of granular base pathways. As paving pills in Hong Kong recycled aggregates were utilized. The recovered aggregate is utilized by the housing department as standard paving blocks (2002). Mehus and Lillestl observed that, following laboratory testing, recycled concrete aggregates may be utilized as a recharge material in the pipe sector, as well. The Norwegian Building Research Institute. Figure 1.2 shows diagrammatically the natural and recycled aggregates.



Figure 1.2 Natural and Recycled Aggregates

Basic Properties of Concrete with Recycled Concrete Aggregate

The most significant features of the recycled (RCA) and the urban mix of recycled concrete (RAC) combination are briefly presented in this research on the basis of experimental data. Recommendations are also given for the manufacture of RACs. A specific quantity of mortar and cement is transferred from the genuine concrete with the stone particles in recycled mix when destroyed concrete are overwhelmed. The reason for the poor quality of RCA compared with an herbal combination is this associated mortar (NA). RCA has households comparable to NA:

- improved water absorption
- reduced bulk density
- reduced unique gravity
- expanded abrasion loss
- multiplied crushing ability
- accelerated quantity of dust debris
- multiplied quantity of natural impurities if concrete is mixed with earth at some stage in building demolition and

- viable content of chemically harmful materials, depending on provider situations in building from which the demolition and crushing recycled aggregate is obtained.




Figure 1.3: schematic flow diagram of small scale concrete recycling plant

Advantages of recycling concrete

The benefits of recycling of concrete are several:

Reduce the quantity of concrete waste stepping into landfill sites.

Reduce using natural assets in production.

Contributes to the surroundings.

- The use of recycled aggregate natural materials saves resources since it is cheaper.
- Recycled trash is manufactured for resale less economically than the transfer of undesirable goods to waste disposal and waste fee incurred.
- A "green" construction material is regarded to be a complete recycled aggregate. The use of recycled aggregates reduces the amount of fresh natural resource aggregates.
- A The need for trash diverting sites to meet sustainable objectives and for waste disposal capacity is increasing, eliminating the use of recovered aggregates to disposal of wastes and fresh storage requirements.

- Studies have also demonstrated that recycled compounds are as durable and safe as native compounds

PROPERTIES OF RECYCLED AGGREGATE CONCRETE

1. Recycled aggregates influence durability and other concrete products in concrete mixtures. As research initiatives to integrate RA into the design industry, the following categories may be classified as:
 2. Policies, costs and benefits: aims at standardizing particular use of RA, highlighting capital costs and highlighting environmental and economic advantages. The main benefits of utilizing recycled materials in the construction industry are conservation of the land and natural resource management.
 3. Human and technological evaluation of RA characteristics. Concrete manufacture including absorption (crash form, amount of crushing stages), size and gradation overall, basic severity, density, consistencies of mortar, pollution content and grade, agglomeration power and abrasive strength, key factors that affect RA use. In particular Variations in load-related RA products influencing the RA-formed concrete property combined with crushing, corrosion, and contaminants including wood and plastic components. Depart from RA Mortar, become less dense, more absorbed and have a significant loss of LA. Moreover, by mass and alkaline content of less than 3.5 kg/m³, the amount of sulfate and alkaline ingredients can be controlled by a maximal level of 0.8-1.0 percent ("Tam et al. 2008; De Juan and Gutiérrez 2009; McNeil & Kang 2013; De Brito and Saikia 2013; Akbarnezhad et al. 2014; Silva et al. 2014").
 4. Composition and proportioning of the mixtures: direct volume substitution, weight substitution and equal mortar substitution, these are among the methods to create RA blends. The blending step also affects the overall concrete characteristics. In addition, the amount of substitutes and pre-harvester techniques showed improved characteristics of RA concrete (Tam et al. 2007a, b; Cabral et al. 2010; Fathifazl et al. 2009; Knaack and Kurama 2013; Wardeh et al. 2014).
 5. New, and hardened RA concrete assessment: a number of methods are evaluated for fresh, hardened cement with RA. Optimizations were also investigated to determine the percentage of RA that may be utilized without affecting short-term and long-term outcomes. Data-based design methods were also drawn up from several sources. The use of repressed aggregates usually reduces all mechanical characteristics to influence new stage and concrete durability because to excessive absorption and porosity (Xiao et al. 2006; Yang et al. 2008; Kwan et al. 2012; Manzi et al. 2013; Akbarnezhad et al. 2013; Ulloa et al. 2013; Xiao et al. 2014; McNeil and Kang 2013; Silva et al. 2014).
 6. Improve RA concrete quality: long-term and durability issues are barriers to the adoption of RA in many applications. A concrete may consist of chloride conductance, permeability of oxygen and dry water, carbonating depth, alkaline aggregate reaction, sulphate resistance, shrinkage and creeping performance, abrasive resistance and freeze resistance. The huge number of holes leading to high permeability and water absorption made of concrete with RA is usually much less durable. Thanks to the cement paste on the surface, significant water absorption is necessary. Before combination, however, conditions for saturated dry surface (SSD) are established. This may be offset. This may not be feasible in certain sectors of mass production. Aggregate absorption may thus be considered during the mixing design phase by change in the water the recycled aggregate consumes. Surface coating was another way of protecting absorption and improving characteristics (Olorunsogo and Padayachee 2002; Zaharieva et al. 2003; Levy and Helene 2004; Ann et al. 2008; Yang et al. 2008; Abbas et al. 2009; Thomas et al. 2013; Lederle and Hiller 2013; Fathifazl and Razaqpur 2013; Xiao et al. 2014; Ryou and Lee 2014). Many research projects have also demonstrated that the use of extra cement (SCM) as a replacement for the cement or as an addition of weight may enhance concrete's durability by improving pores and reducing the volume of pores. Fly ash, (25-35%), silica (10%), and ground granulate slaked oven blasting ovens (up to 65%) are the most common SMCs used to enhance concrete strength and durability characteristics (Berndt 2009; Kou and Poon 2012; Amorim et al. 2012; Eisa 2014).
 7. Crystalline grid, bond characteristics, Interfaces Zone (ITZ): Due to high porosity and absorption capability of highly recycled components, porous microstructure was revealed during the investigation near the Interfacial Transformation Zone (ITZ) Furthermore, potential breaking of hazardous aggregates on the surface may cause concrete fractures, cement unification and decreased add-ons because of grinding and treatment as well as exposure to specific chemicals and deposits. The blending stage, lower w/c ratio and inclusion

of the SCM will enhance IT-Z and bonding properties of recycled concrete.

CONCLUSION

This study identifies the main reasons of the concrete demolition substitution with ground concrete aggregates. The research has shown that disposal trash may successfully be used as an alternative in the building industry to partially replace natural aggregates. A demolition of the material is a waste form which, as a substitute for natural coarse concrete aggregates, is mixed with other materials. The use of destroyed aggregates of concrete as a foundation of road material reduces pollution from trucks.

REFERENCES

- [1] Gokce A., Nagataki S., Saeki T., Hisada M. (2014), "Freezing and thawing resistance of air-entrained concrete incorporating recycled coarse aggregate: The role of air content in demolished concrete", *Cement and Concrete Research*, 34, pp. 799 – 806.
- [2] Preethy K Thomas, Binu M Issac, Deepak John Peter (2015), "Assessment of Demolished Concrete as Coarse Aggregate in Geopolymer Concrete", *International Journal of Advance Research and Engineering*, Vol. 4, Issue 1.
- [3] Prakash Somani, Brahmtoosh Dubey, Lavkesh Yadav, Jitendra Kumar, Abhishekkumar (2016), "Use of demolished concrete waste in partial replacement of coarse aggregate in concrete", *SSRG International Journal of Civil Engineering*, Volume 3, Issue 5, May 2016.
- [4] Kasai Y. (2009), "Studies into the use of demolished concrete in Japan, re-use of concrete and brick material", *EDA/RILEM demo-recycling conference proc.* 22.
- [5] Tavakoli M. P. Soroushian (1996), "Strength of recycled aggregate concrete made with using field-demolished concrete as aggregate", *ACI Materials Journal*, 93 (2), pp. 182 – 190.
- [6] Topcu I.B. (1995), "Using waste concrete as aggregate", *Cement and Concrete Research*, 25, pp. 1385–1390.
- [7] Topcu I.B., Sengel S. (2014), "Properties of concretes produced with waste concrete aggregate", *Cement and Concrete Research*, 34, pp. 1307–1312.
- [8] Umesh Dhargalkar (2014), "Design of a simply supported one-way slab loaded by a strip load along the span", *The Indian Concrete Journal*, pp. 117-118.
- [9] Xiao Jianzhuang, Jiabin Li, Ch. Zhang (2005), "Mechanical properties of recycled aggregate concrete under uniaxial loading", *Cement and Concrete Research*, 35, pp. 1187 –1194.
- [10] Zaharieva R, F. Buyle-Bodin, F. Skoczylas, E. Wirquin (2003), "Assessment of the surface permeation properties of recycled aggregate concrete", *Cement and Concrete Composites*, 25, pp. 223–232.

Corresponding Author

Patil Uday Shankar*

Research Scholar, University of Technology, Jaipur

udayshubu@gmail.com