

# A Study on the Applications of Synthetic Zeolites

Dr. H. V. Bakshi\*

Associate Professor & Head, Department of Physics, ACS College Shankarnagar District-Nanded (MS)

**Abstract – Zeolites and zeolite rocks are commonly used in different industrial applications. Synthetic zeolites present an attractive material for environmental applications because of their high abundance, availability and low costs. Depending on geological settings and conditions during mineral formation, Synthetic zeolite deposits usually represent a heterogeneous mixture of zeolite minerals together with varying amounts of gangue minerals (e.g. quartz, feldspars and phyllosilicates). Hence, profound mineralogical knowledge and a detailed characterization of Synthetic zeolites are essential for tapping their full potential in any practical application. However, this is rarely done as detailed mineralogical characterizations are elaborate and often neglected in favour of bulk chemical analyses (e.g. XRF).**

**Keywords: Zeolite, Characterization, Synthetic**

-----X-----

## INTRODUCTION

An analytical protocol has been developed for the detailed characterization of Synthetic zeolites for ammonium exchange consisting of a combination of mineralogical and chemical methods and is exemplarily demonstrated. The methodology comprises mineralogical investigations with X-ray diffraction (XRD) and electron microprobe analyses (EPMA) to provide qualitative data on mineral compositions and in-situ analysis of mineral chemistry (Si/Al-ratio, cation contents).

The examinations are accompanied by bulk chemical analysis (XRF) as well as thermoanalytical investigations (TG/DSC) to distinguish between certain zeolite minerals. Finally, ion exchange experiments for ammonium have been carried out to determine the cation exchange capacity (CEC) of zeolite samples for a defined range of concentrations.

Zeolites are hydrated aluminosilicates with exchangeable cations and open channel systems in their lattice. They consist of infinitely extending three dimensional networks of  $\text{SiO}_4^{4-}$  and  $\text{AlO}_4^{3-}$  tetrahedra linked by shared oxygen atoms.

The frameworks form voids or cages and channels in which exchangeable cations can enter. Due to substitution of tetravalent silicon by trivalent aluminium charge deficiency has to be balanced by incorporation of loosely bound monovalent and divalent cations of alkali and alkaline earth elements.

Additionally, water can reversibly enter these structures forming partial hydration spheres around the cations where the negative dipole of the water molecules point towards the positively charged monovalent and divalent cations.

The more silica is substituted by aluminium, it is expressed by the Si/Al ratio, the higher the ability to incorporate cations which enhance the properties of zeolite minerals as ion exchangers. Beside 232 synthetic zeolites (molecular sieves) 67 different mineral species of Synthetic zeolites subdivided into 28 different framework types are currently known. Among them, clinoptilolite is one of the most abundant zeolites and widely used in various applications.

Clinoptilolite belongs to the HEU structure type and forms a continuous solid solution series with heulandite. According to IMA (International Mineralogical Association) nomenclature heulandite has Si/Al <4 and clinoptilolite has Si/Al >4.

The microporous structure of their framework as well as their capability to selectively exchange ions of different size and valence have made zeolites interesting for many industrial applications. Synthetic zeolites are widely applied in the construction and building materials industry, water and wastewater treatment, environmental remediation as well as agriculture, consumer products and medical applications.

Clinoptilolite is the main zeolite used for commercial applications, while chabazite and mordenite are used in smaller quantities. Zeolitic tuffs are used as additives in cement and concrete to neutralize excess

lime, but can also be thermally expanded to form light weighed insulation materials.

## APPLICATIONS OF SYNTHETIC ZEOLITES

Large-scale cation-exchange processes for water treatment using Synthetic zeolites were described in the early 1970s. Synthetic zeolites have advantages over other cation exchange materials such as commonly used organic resins, because they are cheap, exhibit excellent selectivity for different cations at low temperatures, are compact in size and allow simple and cost-efficient maintenance in full-scale applications.

Although synthetic zeolites generally have higher cation-exchange capacities, Synthetic zeolites exhibit a greater selectivity for ammonium what makes them an interesting adsorption reagent for nitrogen removal and recovery.

Furthermore, Synthetic zeolites were extensively studied for the removal of heavy metals from municipal, agricultural and industrial waste waters including soil effluents and acid mine drainage. Especially, Synthetic clinoptilolite is a selective ion exchange for ammonium and this has prompted its use in soil amendment and remediation, swimming pools and fish farming. Further potential uses for clinoptilolite are in energy storage and nitrogen recovery.

Synthetic zeolites commonly form as low-temperature alteration products in a variety of rocks, but the most important deposits are found in volcanoclastic and sedimentary rocks. Depending on the geological setting and physico-chemical conditions during mineral formation, zeolite deposits usually represent a heterogeneous mixture of zeolite minerals together with gangue minerals like quartz, feldspars and phyllosilicates (mica, clay minerals).

Hence, geological factors control the stability of zeolite phases (i. e. which zeolites form) as well as the type and amount of gangue minerals present and have a strong influence on the quality and applicability in technical processes. Prior to any technical application a detailed characterization of these materials is therefore necessary in order to understand performance and behaviour within any practical application.

The enormous diversity of zeolites and varying experimental setups and characterization methods make it difficult to compare the results especially when proposed applications are not standardized.

Therefore, a characterization scheme is proposed for technical applications by combined mineralogical and chemical methods and results are presented exemplarily for one selected zeolite sample (Z-01) from an Austrian supplier.

The identification of the crystalline phases of the sample was conducted by XRD using a Philips X'Pert System, Goniometer Type PW3050/60, with CuK $\alpha$  radiation (Chair of Petroleum Geology, Montanuniversität Leoben). The sample was manually powdered in an agate mortar to a final grain size <2  $\mu\text{m}$ . The accelerating voltage was 40 kV and the current 40 mA. Scans were run 5 times by a minimum step size of 0.01 [2 $\theta$ ] between 2.5° to 65° [2 $\theta$ ], scan velocity was 0.5 [2 $\theta$ /min].

The qualitative mineral content was determined on a calculated scan out of all measurements using ICDD-database within the software X'pads. The mineral identification was carried out by at least 2 key peaks allowing a maximum deflection of 0.2 [2 $\theta$ ] for peak matching. R-value (goodness of fitting) of mineral peaks was set below 1.4.

Thermogravimetric (TG) and Differential Scanning Calorimetry (DSC) measurements of the sample were conducted using a STA 449 C (Netzsch Gerätebau GmbH) system (Chair of Process Technology and Industrial Environmental Protection, Montanuniversität Leoben).

The analysis was carried out on about 20 mg of powdered sample material using open type ceramic crucibles. The sample was heated from room temperature up to 1100 °C with a linear heating rate of 5 °C min<sup>-1</sup> in nitrogen atmosphere (flow rate 80 ml min<sup>-1</sup>).

## DISCUSSION

Whole rock chemical composition was determined using a wavelength dispersive X-ray fluorescence spectrometer (WD-XRF AXIOS from PANalytical) at the Chair of General and Analytical Chemistry, Montanuniversität Leoben. Loss on ignition (LOI) was determined gravimetrically by heating about 3 g of material in platinum crucibles to 1000 °C in a muffle furnace for three hours. Fused glass beads were prepared by fusing the ignited sample with Li<sub>2</sub>B<sub>4</sub>O<sub>7</sub> (ratio 1:8).

Zeolite minerals were analysed by electron microprobe (EPMA) using the Superprobe Jeol JXA8200 at the Eugen F. Stumpfl Laboratory (Chair of Resource Mineralogy, Montanuniversität Leoben) using EDS and WDS techniques. Back scattered electron (BSE) images were obtained using the same instrument.

For quantitative analysis (WDS mode) an accelerating voltage of 15 KV, a beam current of 10 nA and a beam diameter of about 1 micron was used. The elements Si, Al, Na, K, Ca, Mg, Fe were analysed using the respective K $\alpha$  lines and the following standards: adularia (Na, K), corundum (Al), quartz (Si), wollastonite (Ca), fluorphlogopite (Mg) and chromite (Fe). Diffracting crystals used were TAP for Na, Mg and Al; PETJ for Si; PETH for K, Ca; LIFH for Fe. The peak and background counting

times were 15 and 5 s for Mg, and 20 and 10 s, respectively for Si, Al, Na, K, Ca and Fe. Detection limits were calculated automatically by the JEOL internal software and are (ppm): Si (240), Al (110), Na (150), K (60), Ca (80) and Fe (330).

The cation-exchange capacity (CEC) for ammonium was measured in batch-experiments with ammoniumsulfate-solutions (Chair of Process Technology and Industrial Environmental Protection, Montanuniversität Leoben). 500 ml of  $(\text{NH}_4)_2\text{SO}_4$ -solutions (concentration range: 500–5000 mg  $\text{NH}_4^+ \text{I}^{-1}$ ) were contacted with 20 g of zeolite in an overhead shaker for 24 h at 20 °C. Liquid samples were taken before and after ion-exchange and filtrated by syringe filters (0.22  $\mu\text{m}$ ). Ammonium was analysed via Kjeldahl-method using boric acid and HCl/Tashiro's indicator for titration. The difference in the ammonium concentration of the initial and final solution represents the amount of exchanged  $\text{NH}_4^+$  and therefore the CEC for different equilibrium concentrations (exchange isotherm).

The clinoptilolite is characterized by higher calcium, potassium and magnesium and low sodium and iron contents. The framework Si/Al-ratio is 4.61 compared to 4.99 for the bulk rock. Small differences can be noted between the whole rock and mineral chemical data: XRF data show higher values of silica and alkalis indicating the presence of quartz, feldspars and K-rich phyllosilicates in addition to clinoptilolite. The feldspars are Na-plagioclase (albite) and alkalifeldspar (orthoclase); i. e. Ca is mostly hosted in clinoptilolite and not in plagioclase.

$\text{Fe}_2\text{O}_3$  as reported by XRF is hosted by accessory iron hydroxides (goethite?). Because these phases are X-ray amorphous they were not detectable by XRD but they were qualitatively confirmed by EPMA. Iron hydroxides occur as thin layers at the rim of some zeolite grains due to weathering. Angular fragments of plagioclase, quartz and alkalifeldspar (approx. 10–50  $\mu\text{m}$  in size) are surrounded by a finer grained zeolite matrix.

The Si/Al value derived from whole rock data is 4.99 and significantly higher than the Si/Al value determined by in situ-measurement of clinoptilolite by EPMA (4.66). The latter excludes quartz and feldspars and represents the correct Si/Al-ratio for clinoptilolite minerals in the investigated sample. Because Si/Al is one of the chemical key parameters influencing the technical applications of zeolites it is important to use this correct ratio from mineral analyses and not that of the bulk sample.

The maximum  $\text{NH}_4^+$ -loading of 23 mg  $\text{g}^{-1}$  (1.28 meq  $\text{g}^{-1}$ ) was obtained at 5000 mg  $\text{I}^{-1}$  initial solution concentration. This value is in good accordance to literature data for clinoptilolite rich zeolites, although it is difficult to compare CEC-results for different zeolite

samples published in literature as the applied methods are not standardized.

Given a CEC for pure clinoptilolite of 1.75 meq  $\text{g}^{-1}$ , the clinoptilolite content of the sample was estimated to be around 73%. Nevertheless, ammonium uptake did not obtain constant values even at the highest initial concentrations as a result of single batch equilibration. Therefore maximum CEC of the sample was not reached and the proposed value of 73% represented the lower limit of clinoptilolite content in the investigated sample.

Detailed characterization of Synthetic zeolites for technical applications requires a combination of mineralogical and physical/chemical methods, many of which are not standardized. For the characterization of Synthetic zeolites we propose the following scheme of analysis which comprises XRD, TG/DSC and XRF in a first step for a simple qualitative identification of the mineral content, thermal properties and chemical composition.

## CONCLUSION

More elaborate analytical techniques for the detailed characterization include EPMA measurements to determine zeolite mineral composition, Si/Al-ratio and exchangeable cation content as well as ion-exchange studies to obtain the concentration dependent cation exchange capacity. Individual results of this set of analysis provide comprehensive information about the whole sample and enable a detailed review of cross-linked parameters (e. g. Si/Al-ratio, CEC and exchangeable cations).

On the whole, the proposed analytical scheme allows for a detailed characterization of Synthetic zeolites prior to their use in various technical applications and it is a powerful combination of methods for quality assurance and materials testing.

## REFERENCES

- Gottardi, G. (2014). Mineralogy and crystal chemistry of zeolites, in: Sand, L.; Mumpton, F. (eds.): Synthetic Zeolites, Oxford: Pergamon, pp. 31–44.
- Gottardi, G.; Galli, E. (2015). Synthetic zeolites, Berlin: Springer-Verlag.
- Passaglia, E.; Sheppard, R. A. (2011). The crystal chemistry of zeolites, in: Bish, D. L.; Ming, D. W. (eds.): Synthetic zeolites: Occurrence, properties, applications: Reviews in mineralogy and geochemistry (45), Washington, DC: Mineralogical Society of America, pp. 69–116

- Deer, W. A.; Howie, R.; Wise, W. S.; Zussmann, J. (2014). Rock forming minerals Volume 4B: Framework silicates: Silica minerals, Feldspathoids and the Zeolites, London: Geological Society of London.
- Armbruster, T.; Gunter, M. (2011). Crystal Structure of Synthetic Zeolites, in: Bish, D. L.; Ming, D. W. (eds.): Synthetic zeolites: Occurrence, properties, applications: Reviews in mineralogy and geochemistry (45), Washington, DC: Mineralogical Society of America, pp. 1–68
- Baerlocher, C.; McCusker, L. B.; Olson, D. H. (2015). Atlas of Zeolite Framework Types, 6th ed., New York: Elsevier Science Limited.
- Wang, S.; Peng, Y. (2010). Synthetic zeolites as effective adsorbents in water and wastewater treatment, Chemical Engineering Journal, 1, pp. 11–24
- Polat, E.; Karaca, M.; Demir, H.; Onus, A. N. (2014). Use of Synthetic zeolite (clinoptilolite) in agriculture, J. Fruit Ornament. Plant Res. Special ed., 12, pp. 183–189.
- Hey, M. H.; Bannister, F. A. (2015). Studies on zeolite. Part VII. "Clinoptilolite", a silica-rich variety of heulandite, Mineralogical Magazine, 23, 2015, pp. 556–559.
- Coombs, D. S. (2015). Recommended nomenclature for zeolite minerals: Report of the Subcommittee on zeolites of the International Mineralogical Association, Commission on New Minerals and Mineral Names, The Canadian Mineralogist, 35, pp. 1571–1606.

---

### Corresponding Author

**Dr. H. V. Bakshi\***

Associate Professor & Head, Department of Physics,  
ACS College Shankarnagar District-Nanded (MS)